

Please type a plus sign (+) inside this box → +

PTO/SB/05 (4/98) Approved for use through 09/30/2000. OMB 0651-0032 U

Under the Paperwork Reduction Act of 1995, no persons are required to	o respo	Pate nd to a collect	nt and ion of ii	Trademark O nformation un	fice: U.S. less it disp	DEPARTMENT OF COMM plays a valid OMB control nu	mper
UTILITY		Attorney Docket No.			0694-134		
PATENT APPLICATION		First Inventor or Application Identifier Yoshio Hashibe					
		Title Fire-Protection Glass Panel With a Heat Shie				ith a Heat Shielding	ļ
(Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))	Expre.	ss Mail Labe	l No.		EL46	7166250US	
APPLICATION ELEMENTS See MPEP chapter 600 concerning utility patent application contents	Ī	ADD	RESS	6 TO: Box	Patent A	mmissioner for Patents pplication DC 20231	=
Fee Transmittal Form (e.g., PTO/SB/17) (Submit an original and a duplicate for fee processing)	-	5.	Micro			gram (Appendix)	
2. Specification [Total Pages 12 (preferred arrangement set forth below)]1			and/or Amin e, a <i>ll neces</i>		equence Submission	
- Descriptive title of the Invention		a.	Ш	Computer	Readab	le Copy	
- Cross References to Related Applications - Statement Regarding Fed sponsored R & D		b.		Paper Cop	y (identi	ical to computer copy)	
- Reference to Microfiche Appendix		C.	П	Statemen	verifying	g identity of above copie	s
- Background of the Invention			cco	MPANYIN	G APPI	LICATION PARTS	
- Brief Summary of the Invention		7.				r sheet & document(s))	
Brief Description of the Drawings (if filed) Detailed Description		8.	37 C.	F.R.§3.73(b) Statem	ent Power of	
- Claim(s)				there is an			
- Abstract of the Disclosure	_	9				ment (if applicable)	
3. Prawing(s) (35 U.S.C. 113) [Total Sheets 2	1	10.	State	nation Disck ment (IDS)/I	PTO-144	9 Copies of IDS Citations	
Oath or Declaration [Total Pages 2	_]]	11.		ninary Amer			
a. Newly executed (original or copy)		12.		n Receipt P <i>Ild be speci</i> .		(MPEP 503) mized)	
b. Copy from a prior application (37 C.F.R. § (for continuation/divisional with Box 16 complete	1.63(c		* Sma	Il Entity		ement filed in prior applic	cation
DELETION OF INVENTOR(S)		13.	(PTO/	ment(s) SB/09-12)		us still proper and desire	d
" Signed statement attached deleti inventor(s) named in the prior appli		14.		ied Copy of eian priority		Document(s)	
see 37 C.F.R. §§ 1.63(d)(2) and 1.3	33(b).	15.				0 and \$ 690.00	
PHOTE FOR ITEMS 1 & 13: IN ORDER TO BE ENTITLED TO PAY SMALL FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), E UF ONE FILED IN A PRIOR APP! (CATION IS RELIED UPON (37 C.F.R. §	XCEPT						
16. If a CONTINUING APPLICATION, check appropriate box	, and s	apply the requ	isite inf	ormation belo	w and in a	a preliminary amendment:	_
Continuation Divisional Continuation-in	-part (C	IP) of	prior a	pplication No:		J	
Prior application information: Examiner For CONTINUATION or DIVISIONAL APPS only: The entire disc	losure o	of the prior a	plicati	Group / Art on, from whi		th or declaration is supplie	ed
under Box 4b, is considered a part of the disclosure of the acci reference. The incorporation can only be relied upon when a p	ompany	ring continua	tion or	divisional a	plication	and is hereby incorporate	ed by
17. CORRESPO							
Customer Number or Bar Code Label (Insert Customer No	. or Atta	ch bar code k	bel her		Z Com	espondence address below	
Hopgood, Calimafde, Kalil & Judlowe	9, L.L.	P.					
Name							
Address 60 East 42nd Street							
Nous York	. 1	NV				10165	
City New York Sta		NY (212) 551	500			10165 (212) 949-2795	
	e	(212) 051	-3000	,	rax		$\overline{}$
Name (PrintType) Bradley N. Ruben		Regi	stration	No. (Attorneys	(gent)	32,058	_

Signature

Burdah Nour Statement: This firm is astimated: 'a take Off hour to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chef Information Office, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Some Patent Application, Washington, DC 20231.

PTO/SB/17 (12/99) Approved for use through 09/30/2000. OMB 0651-0032 of Patent and Trademark Office U.S. DEPARTMENT OF COMMERCE U.s. selection of information unless it diseases a said OMB control number. The

Inder the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.					
FEE TRANSMITTAL	Complete if Known				
	Application Number	NA NA			
for FY 2000 Patent fees are subject to annual revision. Small Entity payments <u>must</u> be supported by a small entity statement, otherwise large entity fees must be paid. See Forms PTO(SBI09-12. See 37 C.F.R. §§ 1.27 and 1.28.	Filing Date	NA			
	First Named Inventor	Yoshio Hashibe			
	Examiner Name	NA			
	Group / Art Unit	NA NA			

TOTAL AMOUNT OF PAYMENT	(\$) 730.00	Attorney Docket No. 0694-134								
METHOD OF PAYMENT	FEE CALCULATION (continued)									
	The Commissioner is hereby authorized to charge indicated fees and credit any overpayments to:				L FE Entity Fee (\$)		Fee D	escription		Fee Paid
Account Number 08-277	6	105	ie (\$) 130	205	65	Surcha	rae - late f	iling fee or oa	ath	
Deposit Account Hopgood, Calimafde, Ka	alil & Judlwe, LLP	127	50	227	25	covers	sheet.	provisional fili	ng fee or	
Name		139	130	139	130		nglish spec			
Charge Any Additional Fee I Under 37 CFR §§ 1.16 and	Required 1.17	147 112	2,520 920*	147 112	2,520 920*	Reque		st for reexami cation of SIR		
2. Payment Enclosed: Check Order	Other	113	1,840*	113	1,840*	Reque		ation of SIR	after	
FEE CALCULATI	ON	115	110	215	55			y within first i		
	<u> </u>	116	380	216	190			y within seco		
BASIC FILING FEE Large Entity Small Entity		117	870	217	435			ly within third		
Fee Fee Fee Fee Descri	ption Fee Paid	118	1,360	218	680			ly within fourt		-
Code (\$) Code (\$) 101 690 201 345 Utility filing fe		128	1,850	228	925			ly within fifth	month	<u> </u>
106 310 206 155 Design filing	030.00	119	300	219	150		of Appeal			
107 480 207 240 Pia: filing fe		120	300	220	150	_		pport of an a	ippeal	
108 690 208 345 Reissue filing		121	260	221			st for oral I			-
114 150 214 75 Provisional fi		138	1,510	138	1,510				e proceeding	
		140	110	240	55			 unavoidable 		
SUBTOTAL (1)	(\$) 690.00	141	1,210	241	605			- unintention	al	
2. EXTRA CLAIM FEES			1,210	242	605		ssue fee (d	or reissue)		
Extra Claims	Fee from Fee Paid	143		243	215	_	issue fee			
Total Claims 8 -20** = 0 X	18 = 0	144		244	290		ssue fee			
Independent 1 - 3** = 0 X	78 = 0	122			130	Petitio	ns to the C	ommissioner		
Multiple Dependent	ŧ	123		123	50	Petitio	ns related	to provisional	applications	
**or number previously paid, if greater, F	or Reissues, see below	126	240	126	240	Submi	ssion of Int	formation Dis	closure Stmt	
Large Entity Small Entity Fee Fee Fee Fee Fee De Code (\$) Code (\$)	scription	581		581	40	Recon	ding each p ty (times n	atent assign umber of pro	ment per perties)	40.00
103 18 203 9 Claims in exc		146	690	246	345	Filing	a submissi R § 1.129	on after final	rejection	
	claims in excess of 3 indent claim, if not paid	149	690	249	345	Fores	ch addition	nal invention t		
	dependent claims	Othe	r fee (sp	ecify)		exami	ned (37 CF	R § 1.129(b)		
110 18 210 9 ** Reissue cl	aims in excess of 20 iginal patent		r fee (sp							
SUBTOTAL (2)	(\$) 0	*Red	luced by	Basic	Filing	Fee Pai	d S	SUBTOTAL	. (3) (\$)	40.00
SUBMITTED BY								Complete (i	f applicable)	
Name (Print/Type) Bradley N. Ruben			Regisi (Attorni			32	,058	Telephone	(212) 551	-5000 x 4081
Signature	Bradley 1	v.	/L	_				Date	2 Octo	ber 200
WARNING:		_								

Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time year en required to complete his form should be sent to the Chef information Officer, Palent and Tablemark Office, Washington, DC 20231. DO NOT SEND TESS OR COMPLETED FORMS TO 1 HIS ADDRESS. SEND TO: Assistant Commissioner for Palents, substraight to 2 20231.

FIRE-PROTECTION GLASS PANEL WITH A HEAT SHIELDING CHARACTERISTIC

Background of the Invention:

The present invention relates to a fire-protection glass product such as a glass panel for use as a building material to prevent spread and expansion of fire and to assure the safety during escape from fire and, in particular, to a fire-protection glass product having a heat shielding characteristic.

As a glass product called a fire-protection glass, a wire glass, a tempered glass, and a crystallized glass are known and already put into practical use. Such fire-protection glass has heat resistance and not only serves to shield flames and smokes upon occurrence of fire but also serves as a transparent window for assuring an inside view. However, the fireproof glass can not substantially attenuate heat radiation towards an unburnt area. Such heat radiation may cause the spread of fire to a next room and the difficulty in assuring a safe escape route.

In order to shield the heat radiation, proposal has been made of a fire-protection glass product having a multilayer structure comprising two glass plates 1a and 1b with a gel layer 5 interposed therebetween as illustrated in Fig. 1. Upon occurrence of fire, the gel layer 5 foams, i.e., produces bubbles to exhibit a heat shielding characteristic.

However, the above-mentioned fire-protection glass product uses a large amount of a gel material so that a high material cost is required. In addition, since the above-mentioned glass product is large in thickness and heavy in weight, a high construction cost is also required. Moreover, upon

occurrence of fire, the gel layer foams in several minutes to become opaque. This means that the function of assuring the inside view as the transparent window can not substantially be expected.

Summary of the Invention:

It is therefore an object of the present invention to provide a fireprotection glass product which has both fireproof and heat shielding characteristics, which is light in weight and small in thickness to be easily equipped, and which does not require a gel layer.

According to one aspect of the present invention, a fire-protection glass product having a heat shielding characteristic comprises a plurality of fireproof glass plates, a resin intermediate layer interposed therebetween, and a heat-ray reflection film or IR reflection film formed on the surface of at least one of said glass plates. The heat-ray reflection film has a reflectance of 70% or more for a light of the wavelength of 2500nm and an average transmittance of 60% or more for visible rays.

At least one of the fireproof glass plates may be made of a heatresistant transparent crystallized glass.

In the fire-protection glass product according to this invention, the heatray reflection film, which is transparent, is formed on one or both of opposite
surfaces of at least one fireproof glass plates. With this structure, heat rays
produced upon occurrence of fire are reflected by the heat-ray reflection film to
suppress heat emission and to attenuate heat radiation to the next room.
Furthermore, a resin material used as the intermediate layer is darkened by
temperature rise upon occurrence of fire and absorbs the heat rays. At usual
times, the fire-protection glass product of this invention serves as a safety glass
by provision of the intermediate layer which prevents shattering or scattering of
cracked glass pieces when the glass product is damaged or broken by collision
or impact.

The heat-ray reflection film has a reflectance of 70% or more for a light of a wavelength of 2500nm. Upon occurrence of fire, the temperature of a burnt area falls within a range between 800℃ and 900℃. At this time, an energy distribution of the heat ray radiated therefrom corresponds to a light of a wavelength of 2000 to 3000nm. If the heat-ray reflectance is 70% or more for a light of the wavelength of 2500nm, the heat-ray reflection film reflects the heat radiation upon occurrence of fire and sufficiently suppresses heat radiation into the unburnt area. On the other hand, if the heat-ray reflectance is 70% or less for a light of the wavelength of 2500nm, the heat-ray reflection film cannot substantially attenuate the heat radiation so that heat-shielding characteristic is insufficient. The heat-ray reflection film has such a spectral characteristic or a light selectivity that it has reflectance of 70% or more, 50% or more, and 80% or more for spectra lights of wavelengths of 2500nm, 1500nm and 3000nm, respectively.

The heat-ray reflection film has an average transmittance of 60% or more for visible rays (400nm to 700nm). If the average transmittance for the visible rays is less than 60%, light transparency of the film is so low so that a sufficient range of view or sight cannot be assured through the glass panel with the film. This deteriorates the function of the glass panel as a window. Preferably, the heat-ray reflection film has an average reflectance of 15% or less for visible rays.

As the heat-ray reflection film having the above-mentioned characteristics, use is most preferably made of an indium oxide film containing tin, an antimony oxide film containing tin, a tin oxide film containing fluoride, or a tin oxide film containing antimony. Alternatively, a ZnO-based transparent film can also be used. These films can be deposited on the glass plate by sputtering, spraying, dipping, or the like.

The heat-ray reflection film has a thickness between 1000Å and 15000Å. If the thickness is not greater than 1000Å, the heat-ray reflectance at the wavelength of 2500nm tends to fall within the range not greater than 70%. If the thickness is not smaller than 15000Å, the average transmittance for visible rays tends to fall within the range not greater than 60%.

As the fireproof glass plate, use may be made of a low-expansion crystallized glass, a borosilicate glass, a strengthened glass, and the like, alone or in combination. In particular, the low-expansion crystallized glass is preferable as the glass plate because it is resistant against the fire continuing for a longer time period and does not break even if it is spayed water by a sprinkler.

Upon occurrence of fire, the resin intermediate layer serves to absorb heat rays because the resin material is carbonized (blackened) by incomplete combustion. At normal times, the resin intermediate layer serves to assure the safety by preventing the release and the drop of the glass pieces when the glass plate is broken. As the resin material, use may be made of fluorocarbon resin, polycarbonate resin, polyethylene terephthalate resin, and the like.

In order to achieve a higher heat shielding characteristic, the fireprotection glass product may have a double-glazing structure including an additional glass plate attached through an air layer. The fireproof glass plate may be combined with a soda-lime glass plate.

Now, embodiments of this invention will be described in detail with reference to the drawing.

Brief Description of the Drawings:

Fig. 1 is a sectional view of a conventional fire-protection glass panel having a gel layer;

Fig. 2 is a sectional view of a fire-protection glass panel according to an embodiment of this invention; and

Fig. 3 is a sectional view for describing a multilayer glass panel using the fire-protection glass panel illustrated in Fig. 2.

Description of the Preferred Embodiments:

Description will now be made as regards embodiments of this invention with reference to the drawing.

As illustrated in Fig. 2, a fire-protection glass panel having a heat shielding characteristic comprises two fireproof glass plates 1a and 1b, a resin intermediate layer 2 interposed between the glass plates 1a and 1b, and a heat-ray reflection film 3 formed on an outer surface of the fireproof glass plate 1a. The heat-ray reflection film 3 has a reflectance of 70% or more for a light of the wavelength of 2500nm and an average transmittance of 60% or more for visible rays.

Referring to Fig. 3, a multi-layer glass panel comprises the fire-protection glass panel illustrated in Fig. 2 and an additional fireproof glass plate 1c with an air layer 4 interposed therebetween. This structure achieves a higher heat shielding characteristic. The fireproof glass plate may be combined with a soda-lime glass plate.

Now, specific examples of the fire-protection glass panel of this invention will be described in detail together with comparative examples.

Example 1

At first, preparation was made of two heat-resistant transparent crystallized glass plates (FIRELITE manufactured by Nippon Electric Glass Co., Ltd.) each of which has a dimension of $950\times600\times4$ mm and a thermal expansion coefficient of -5×10^{-7} °C.

Subsequently, an ITO (indium-tin oxide) film was deposited onto one surface of one of the glass plates by the use of a sputtering apparatus at a temperature of 350 $^{\circ}$ C. The ITO film had a thickness of 4000 Å.

Then, each glass plate was cut into a sample piece having a dimension of $900\times600\times4$ mm. Using the sample piece, the spectral characteristic of the glass plate after the above-mentioned deposition was measured by the use of a spectrophotometer. Herein, the reflectance was measured as a total internal reflectance using an integrating sphere while the transmittance was measured without using the integrating sphere.

As a result, the reflectance for a light of the wavelength of 2500nm was equal to 95% and the average transmittance for visible rays was equal to 81%. Thus, these values were preferable as external appearance of the film.

Subsequently, as a resin intermediate layer, preparation was made of a fluorocarbon resin film comprising a copolymer containing 40 weight% of tetrafluoroethylene (TFE), 20 weight% of hexafluoropropylene (HFP), and 40 weight% of vinylidene fluoride (VDF) and having a chain molecular structure. The film had a thickness of $500\,\mu$ m. The resin film was placed between the fireproof glass plates and subjected to thermo-compression bonding to obtain the fire-protection glass panel as illustrated in Fig. 2. The thermo-compression bonding was carried out by holding the resin film at a predetermined temperature for 15 minutes under a pressure of 1.27MPa.

Example 2

Preparation was made of two tempered borosilicate glass plates having a dimension of $950\times600\times4$ mm, similar to that of Example 1.

Subsequently, one of the glass plates was heated by an electric furnace to a temperature of 600° C. Then, stannic chloride solution containing 1% antimony was applied onto one side surface of the above-mentioned glass plate by the use of a spraying device to deposit an antimony-containing tin oxide film. The tin oxide film thus obtained had a thickness of 2500 Å.

In the manner similar to that mentioned in conjunction with Example 1, measurement was made of the spectral characteristic of the glass plate after

the above-mentioned deposition. As a result, the reflectance for a light of the wavelength of 2500nm was equal to 78% and the average transmittance for visible rays was equal to 74%. These values were preferable as external appearance of the film.

Thereafter, as the resin intermediate layer, preparation was made of a polyethylene terephthalate resin film having a thickness of 200 μ m and having adhesive layers formed on opposite surfaces thereof. By the use of the resin film, the two glass plates were adhered to each other to obtain the fire-protection glass panel as illustrated in Fig. 2.

Comparative Example

For the purpose of comparison, preparation was made of a tempered borosilicate glass plate similar to that in Example 2.

Then, in the manner similar to Examples mentioned above, measurement was made of the spectral characteristics of the glass plate. As a result, the reflectance for a light of the wavelength of 2500nm was equal to 7% and the average transmittance for visible rays was equal to 85%.

Evaluation

Each sample of Examples 1 and 2 and Comparative Example was subjected to a heat-shielding test.

The heat-shielding test was performed in the following manner. At first, each sample was fixed to a frame at its end surfaces so as to avoid the end surfaces from being heated, and was arranged in front of a flat heating furnace. Then, the sample was heated in accordance with a standard heating curve provided in the Official Notification No.1125 of the Ministry of Construction of Japan. By the use of a heat flow sensor located at a distance of 0.5m from the center of an unheated surface of the sample, the maximum heat received 'thereat (W/cm²) was measured after lapse of 60 minutes. Those samples of Examples 1 and 2 were tested for a case A in which the heat-ray reflection film

was positioned on a heated side or a side facing the heating side and a case B in which the heat-ray reflection film was positioned on the opposite or unheated side. The results are shown in Table 1.

Table 1

	Table 1				
	Example 1	Example 2	Comparative Example		
Reflectance Average for Visible Rays	12	19	6		
1500nm	60	55	6		
2500nm	95	78	7		
3000nm	98	83	7		
Transmittance Average for Visible Rays	81	74	85		
1500nm	8	15	86		
2500nm	3	18	87		
3000nm	2	15	88		
Heat Received (W/cm²)					
Case A	1.0	1.2	3.1		
Case B	1.1	1.3	-		

As is obvious from Table 1, each of the Examples exhibited the heat received as low as 1.0-1.3W/cm² after lapse of 60 minutes (925°C) after start of heating. Furthermore, each of the Examples was maintained for more than about 15 minutes after start of heating to allow the other side to be seen through it.

For a conventional fire-protection glass panel (manufactured and sold by SAINT-GOBAIN CERAMIQUES IND. (FRANCE) under the trade name of CONTRAFLAM) which comprises the gel layer 5 interposed between two glass

plates 1a and 1b as illustrated in Fig. 1, the similar heat shielding test was performed. As a result, the heat received was sufficiently low but foaming of the gel layer 5 occured so that the other side can no longer be seen through it after lapse of about 4 minutes after start of heating.

In the fire-protection glass product according to this invention, the heat radiation upon occurrence of fire is reflected by the heat-ray reflection film and absorbed by blackening of the resin layer interposed between the glass plates. Therefore, the fire-protection glass product has high heat-shielding characteristic. This suppresses the probability of combustion or ignition of matters present in a room adjacent to the fired room to thereby prevent the spread of fire. In addition, it is possible to assure a safe escape route upon occurrence of fire. Furthermore, since the light transparency can be maintained for a predetermined time duration, the status of fire can be visually confirmed to thereby facilitate lifesaving and fire fighting. Moreover, the fire-protection glass product according to this invention is thin in thickness, light in weight, and low in construction cost and is therefore advantageously used as a building material.

WHAT IS CLAIMED IS:

- A fire-protection glass product having a heat shielding characteristic, comprising:
 - a plurality of fireproof glass plates;
- a resin intermediate layer interposed between adjacent ones of said glass plates;
- a heat-ray reflection film formed on the surface of at least one of said glass plates and having a reflectance of 70% or more for a light of the wavelength of 2500nm and an average transmittance of 60% or more for visible rays.
- A fire-protection glass product as claimed in claim 1, wherein at least one of said fireproof glass plates is made of a heat-resistant transparent crystallized glass.
- A fire-protection glass product as claimed in claim 1, wherein said resin intermediate layer is made of a material selected from fluorocarbon resin, polycarbonate resin, and polyethylene terephthalate resin.
- 4. A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film is formed on at least one of opposite surfaces of said fireproof glass plates.
- 5. A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film is made of a material selected from indium oxide containing tin, antimony oxide containing tin, tin oxide containing fluorine, and tin oxide containing antimony.
- 6. A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film has a thickness between 1000 $\rm \mathring{A}$ and 15000 $\rm \mathring{A}$.
- 7. A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film has a reflectance of 50% or more for a light of a

wavelength of 1500nm and 80% or more for a light of a wavelength of 3000nm, and an average reflectance of 15% or less for visible rays.

 A fire-protection glass product as claimed in claim 1, said glass product having a double-grazing structure including an additional glass plate attached through an air layer.

Abstract of the Disclosure:

A fire-protection glass product having a heat shielding characteristic comprises a plurality of fireproof glass plates, a resin intermediate layer interposed between adjacent ones of the glass plates, and a heat-ray reflection film. The heat-ray reflection film is formed on the surface of at least one of the glass plates, and has a reflectance of 70% or more for a light of the wavelength of 2500nm and an average transmittance of 60% or more for visible rays. The resin intermediate layer is made of a material selected from fluorocarbon resin, polycarbonate resin, and polyethylene terephthalate resin. At least one of the fireproof glass plates may be made of a heat-resistant transparent crystallized glass plate. The heat-ray reflection film may be formed on at least one of opposite surfaces of the fireproof glass plate. The heat-ray reflection film may be made of a material selected from indium oxide containing tin, antimony oxide containing tin, tin oxide containing fluorine, and tin oxide containing antimony. The heat ray reflection film has a thickness between 1000Å and 15000Å. The heat-ray reflection film has a reflectance of 50% or more for a light of a wavelength of 1500nm, a reflectance of 80% or more at a wavelength of 3000nm, and an average reflectance of 15% or less for visible rays.




FIG. 1




FIG. 2




FIG. 3

SOLE INVENTOR

Country

Attomorr's	

Docket No.

DECLARATION OF INVENTORSHIP AND POWER OF ATTORNEY

As the below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below, next to my name.

I believe I am an original, first and sole inventor of the subject matter which is claimed and for which a U.S. Utility Patent is sought on the invention entitled

FIRE-PROTECTION GLASS PANEL WITH A HEAT SHIELDING CHARACTERISTIC the specification of which

x	is attached hereto.		
[]	was filed on		ลร
	Application Serial No.		
	and was amended on		
		(if applicable)	

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims and the drawings presented therein and declare that the subject matter of the claims was part of the invention and was invented before the filing of the aboveidentified original application for such invention.

I hereby claim foreign priority benefits under Title 35, United States Code, §119, of any foreign patent application(s) and PCT International application(s) listed below and have also identified below any foreign patent application(s) having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)

Priority Claimed Application Number Date of Filing No Japan 278023/1999 30 September 1999 [x]

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorneys to prosecute this application and transact all business following attorneys to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: Hopgood, Calimafde, Kalil & Judlowe, a firm consisting of Roy C. Hopgood, Reg. No. 15,245; Eugene J. Kalil, Reg. No. 16,686; John M. Calimafde, Reg. No. 16,895; Stephen B. Judlowe, Reg. No. 21,049; Marvin N. Gordon, Reg. No. 23,094; Francis J. Murphy, Reg. No. 24,537; James M. Rhodes, Jr., Reg. No. 25,229; Dennis J. Mondolino, Reg. No. 27,148; William G. Todd, Reg. No. 28,480; Ira B. Winkler, Reg. No. 29,223; Porter F. Fleming, Reg. No. 31,759; James M. Bollinger, Reg. No. 32,555, Jae H. Kim, Reg. No. 32,907 and Rvian P. Murphy, Reg. No. 34,986 at that firm and Brian P. Murphy, Reg. No. 34,986 at that firm.

SEND CORRESPONDENCE TO:

DIRECT TELEPHONE CALLS TO:

Mr. Jae H. Kim, Esq.

Mr. Jae H. Kim, Esq.

Hopgood, Calimafde et al. 60 East 42nd Street

(212) 986-2480

New York, New York 10165

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true, and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of first joi	nt-inventor YOSHIO HASHIBE
Inventor's signature Date September 26,	yoshio Hashihe
ResidenceGamou-	gun, Shiga, Japan
CitizenshipJapane	se
Post Office Address	c/o NIPPON ELECTRIC GLASS CO., LTD., 7-1, Seiran
	2-chome, Otsu-shi, Shiga 520-8639 Japan
· ·	joint-inventor AKIHIKO SAKAMOTO
Inventor's signature	A. lolant
Date September 26,	2000
Residence Koka-gu	a, Shiga, Japan
Citizenship Japanes	-
Post Office Address .	c/o NIPPON ELECTRIC GLASS CO., LTD., 7-1, Seiran
	2-chome, Otsu-shi, Shiga 520-8639 Japan
Full name of third jo	int-inventor
Inventor's signature	
Date	
Residence	
Citizenship	
Post Office Address	